



VERSA-SPAN™
Roof panel

SECTION PROPERTIES								ALLOWABLE UNIFORM LOADS, psf For various clip spacings (i.e. span values)											
Width, in.	Gauge	Yield ksi	Weight psf	Top in Compression			Bottom in Compression			Inward Load									
				I_{xx} in ⁴ /ft.	I_{xx} (eff) in ⁴ /ft.	S_{xx} in ³ /ft	I_{xx} in ⁴ /ft.	I_{xx} (eff) in ⁴ /ft.	S_{xx} in ³ /ft	2'	2.5'	3'	3.5	4'	4.5'	5'	5.5'	6'	8'
12	24	50	1.47	0.1299	0.1095	0.0907	0.0596	0.0800	0.0638	300.0	240.0	177.2	130.2	99.7	78.8	63.8	52.7	44.3	24.9
12	22	50	1.875	0.1645	0.1401	0.1157	0.0804	0.1048	0.0827	493.2	330.8	229.7	168.8	129.2	102.1	82.7	68.4	57.4	32.3
16	24	50	1.36	0.1020	0.0855	0.0682	0.0451	0.0616	0.0480	225.0	180.0	133.3	98.0	75.0	59.3	48.0	39.7	33.3	18.8
16	22	50	1.71	0.1323	0.1120	0.0825	0.0609	0.0816	0.0623	370.0	249.2	173.1	127.1	97.3	76.9	62.3	51.5	43.3	24.3
18	24	50	1.28	0.0920	0.0769	0.0605	0.0400	0.0551	0.0426	266.3	170.4	118.3	86.9	66.6	52.6	42.6	35.2	29.6	16.6
18	22	50	1.61	0.1200	0.1009	0.0798	0.0540	0.0731	0.0553	328.6	221.2	153.6	112.9	86.4	68.3	55.3	45.7	38.4	21.6

- Theoretical section properties have been calculated per AISI 2012 North American Specification for the Design of Cold-Formed Steel Structural Member. I_{xx} and S_{xx} are effective section properties for deflection and bending.
- Allowable load is calculated in accordance with AISI 2012 specifications considering bending, shear, combined bending and shear and deflection. Allowable load considers a 3 or more equal span condition.
- Allowable load does not address panel weight, fasteners, connection strength or support material.
- Allowable load includes web crippling.
- Load/Span values are based on theoretical computations and not load testing.
- Deflection is **not considered**.
- Allowable loads do not include a 1/3 stress increase for wind.

SECTION PROPERTIES								ALLOWABLE UNIFORM LOADS, psf For various clip spacings (i.e. span values)											
Width, in.	Gauge	Yield ksi	Weight psf	Top in Compression			Bottom in Compression			Inward Load									
				I_{xx} in ⁴ /ft.	I_{xx} (eff) in ⁴ /ft.	S_{xx} in ³ /ft	I_{xx} in ⁴ /ft.	I_{xx} (eff) in ⁴ /ft.	S_{xx} in ³ /ft	2'	2.5'	3'	3.5	4'	4.5'	5'	5.5'	6'	8'
12	24	50	1.47	0.1299	0.1095	0.0907	0.0596	0.0800	0.0638	300.0	240.0	177.2	130.2	99.7	78.8	63.8	52.7	44.3	24.9
12	22	50	1.875	0.1645	0.1401	0.1157	0.0804	0.1048	0.0827	493.2	330.8	229.7	168.8	129.2	102.1	82.7	68.4	57.4	32.3
16	24	50	1.36	0.1020	0.0855	0.0682	0.0451	0.0616	0.0480	225.0	180.0	133.3	98.0	75.0	59.3	48.0	39.7	33.3	18.8
16	22	50	1.71	0.1323	0.1120	0.0825	0.0609	0.0816	0.0623	370.0	249.2	173.1	127.1	97.3	76.9	62.3	51.5	43.3	24.3
18	24	50	1.28	0.0920	0.0769	0.0605	0.0400	0.0551	0.0426	266.3	170.4	118.3	86.9	66.6	52.6	42.6	35.2	29.6	16.6
18	22	50	1.61	0.1200	0.1009	0.0798	0.0540	0.0731	0.0553	328.6	221.2	153.6	112.9	86.4	68.3	55.3	45.7	38.4	21.6

- Theoretical section properties have been calculated per AISI 2012 North American Specification for the Design of Cold-Formed Steel Structural Member. I_{xx} and S_{xx} are effective section properties for deflection and bending.
- Allowable load is calculated in accordance with AISI 2012 specifications considering bending, shear, combined bending and shear and deflection. Allowable load considers a 3 or more equal span condition.
- Allowable load does not address panel weight, fasteners, connection strength or support material.
- Allowable load includes web crippling.
- Load/Span values are based on theoretical computations and not load testing.
- Deflection consideration is limited by a maximum deflection ratio of **L/120** of span.
- Allowable loads do not include a 1/3 stress increase for wind.

SECTION PROPERTIES								ALLOWABLE UNIFORM LOADS, psf For various clip spacings (i.e. span values)											
Width, in.	Gauge	Yield ksi	Weight psf	Top in Compression			Bottom in Compression			Inward Load									
				I_{xx} in ⁴ /ft.	I_{xx} (eff) in ⁴ /ft.	S_{xx} in ³ /ft	I_{xx} in ⁴ /ft.	I_{xx} (eff) in ⁴ /ft.	S_{xx} in ³ /ft	2'	2.5'	3'	3.5	4'	4.5'	5'	5.5'	6'	8'
12	24	50	1.47	0.1299	0.1095	0.0907	0.0596	0.0800	0.0638	300.0	240.0	177.2	130.2	99.7	78.8	63.8	52.7	44.3	24.9
12	22	50	1.875	0.1645	0.1401	0.1157	0.0804	0.1048	0.0827	493.2	330.8	229.7	168.8	129.2	102.1	82.7	68.4	57.4	32.3
16	24	50	1.36	0.1020	0.0855	0.0682	0.0451	0.0616	0.0480	225.0	180.0	133.3	98.0	75.0	59.3	48.0	39.7	33.3	18.8
16	22	50	1.71	0.1323	0.1120	0.0825	0.0609	0.0816	0.0623	370.0	249.2	173.1	127.1	97.3	76.9	62.3	51.5	43.3	24.3
18	24	50	1.28	0.0920	0.0769	0.0605	0.0400	0.0551	0.0426	266.3	170.4	118.3	86.9	66.6	52.6	42.6	35.2	29.6	16.6
18	22	50	1.61	0.1200	0.1009	0.0798	0.0540	0.0731	0.0553	328.6	221.2	153.6	112.9	86.4	68.3	55.3	45.7	38.4	21.6

- Theoretical section properties have been calculated per AISI 2012 North American Specification for the Design of Cold-Formed Steel Structural Member. I_{xx} and S_{xx} are effective section properties for deflection and bending.
- Allowable load is calculated in accordance with AISI 2012 specifications considering bending, shear, combined bending and shear and deflection. Allowable load considers a 3 or more equal span condition.
- Allowable load does not address panel weight, fasteners, connection strength or support material.
- Allowable load includes web crippling.
- Load/Span values are based on theoretical computations and not load testing.
- Deflection consideration is limited by a maximum deflection ratio of **L/180** of span.
- Allowable loads do not include a 1/3 stress increase for wind.

